

## **CHEMICAL RESISTANCE OF VARIOUS GLOVE TYPES**

<b>Chemical</b>	<b>Natural Rubber</b>			<b>Nitrile</b>	<b>PVC</b>	<b>Neoprene</b>
	<b>L</b>	<b>M</b>	<b>H</b>			
Nitric acid 50%	X	X	S	S	G	G
Sulphuric acid 50%	S	E	E	E	E	E
Ethanoic acid 100%	X	F	G	F	F	G
Ammonia "880"	F	G	E	G	E	E
Sodium hydroxide, sat.	F	G	E	F	E	E
Copper(II) sulphate, sat.	F	G	E	G	E	E
Ethoxyethane	X	F	G	G	F	G
Propanone	F	G	E	X	X	E
Methanol	F	E	E	G	G	E
Ethanol	G	E	E	G	F	E
Phenylamine	X	X	S	X	G	S
Petroleum spirit	X	F	G	E	F	G
Methylbenzene	X	X	X	S	F	S
1,1,1-Trichlorethane	X	X	X	S	X	X
Hydrogen peroxide, 100 vols.	G	G	E	G	E	E
Detergent solutions	G	G	G	F	G	E

  

CODE: L=LIGHT WEIGHT	M=MEDIUM WEIGH	H=HEAVYWEIGHT
X=NIL	F=FAIR	G=GOOD
E=EXCELLENT	S=SPLASH ONLY	